

PRODUCT DATA SHEET

Sika® Sigunit® L-53 TH

Alkali Free Liquid Shotcrete Accelerator For Wet or Dry Shotcrete Process

DESCRIPTION

Sika® Sigunit® L-53 TH is a high performance, liquid, alkali-free shotcrete accelerator.

USES

Sika® Sigunit® L-53 TH is suitable set accelerator for dry-process as well as for wet process shotcreting. The main fields of applications are:

- Securing of rock in tunnel and mine construction (preliminary support)
- Rock and slope stabilization
- Dewatering work by dry process
- High quality shotcrete for permanent support by shotcrete

CHARACTERISTICS / ADVANTAGES

Sika® Sigunit® L-53 TH provides the following benefits:

- Alkali free (non-caustic) and classified as non-toxic product
- Fast to very fast setting of shotcrete mixes according to dosage used
- No strength loss of the accelerated concrete if used correctly
- No additional contamination of mountain and ground water due to washed out alkalis
- Large reduction in rebound as long as the spraying is performed according to the state of the art
- Improves bond of shotcrete to rock and concrete, making overhead spray easier
- Free of chlorides, no danger to steel reinforcement and steel fibers

PRODUCT INFORMATION

Packaging	200 L/drums
Appearance / Colour	White milky to grey milky liquid.
Shelf life	3 months from date of production If stored properly in undamaged, original, sealed packaging.
Storage conditions	Store in a cool, dry place. Protected from direct sunlight.
Density	1.41 ± 0.05 kg/l (at temperature 25°C)
pH-Value	2.0 - 3.0 Approx.

APPLICATION INFORMATION

Recommended dosage

Accelerator dosage depends on many factors and actually should be adjusted as per the site conditions met.

It should not be fixed for one time at all!

The dosage of the accelerator would vary according to the scope of work. Typically if the reduction of the rebound (without early strength) is required the dosage would be 2-4%. If early strength is required, dosage would be 4-6%. It would depend as well as on the type of application, vertical (benches) spraying or over-head spraying.

The performance of the accelerator would depend on the cement type, content, age and quality, the W/C of the mix, temperature of the mix, the substrate condition, etc.

As guide line, accelerator dosage – that need to be confirmed by site trial:

Process	Requirement	Dosage
Dry	Rebound reduction or vertical application	~3% by weight of cement
Dry	Early Strength or over-head application	4-6% by weight of cement
Wet	Rebound reduction or vertical application	4-5% by weight of cement
Wet	Early Strength or over-head application	5-6% by weight of cement

Concrete temperature should not be lower than 15°C (especially so for thick layers). Lower temperatures require higher dosages.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LIMITATIONS

When using sulphate resistant cement, strength development may be slower.

- Sika® Sigunit® L-53 TH is not compatible with Sigunit® L20/L62
- Accelerator hoses must be thoroughly cleaned before using Sika® Sigunit® L-53 TH
- Metal parts of the pump coming into contact with Sika® Sigunit® L-53 TH must be stainless steel.
- The set accelerating effect depends on cement content, cement age, cement type, temperature of shotcrete and substrate as well as on layer thickness and shotcreting method.
- A further efficiency parameter of Sika® Sigunit® L-53 TH is the W/C ratio of the concrete mix in wet process or the quantity of water added at the nozzle in dry process.

APPLICATION INSTRUCTIONS

The accelerator will be added and mixed with the other concrete components as follows:

Dry Process

Sika® Sigunit® L-53 TH is supplied from the liquid dosing unit to the mixing tube assembly by means of water under pressure (2-3 bars more than the conveying pressure). The mixing tube assembly being located ~ 2.5 meters behind the nozzle or at the nozzle directly.

Wet Process

Sika® Sigunit® L-53 TH is supplied from the liquid dosing unit to the mixing tube assembly by means of air under pressure (2-3 bars more than the conveying pressure). The mixing tube assembly being located ~ 2.5 meters behind the nozzle or at the nozzle directly.

DISPENSING

Sika® Sigunit® L-53 TH is added thanks to suitable liquid dosing unit such as Aliva AL 403.4 (24-240 lt/h) or AL 403.5 (30-700 lt/h).

Suitable dosing unit type is determined according to cement content, spraying out-put and the accelerator dosage.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA (MYANMAR) LIMITED

No.31, Mahabandula Street, South

Dagon

Kyansittar Yeik Mon Industrial Zone,

Yangon, Myanmar.

Phone: +959 798366081, +951 657970-2

E-mail: myanmar.sales@mm.sika.com

PRODUCT DATA SHEET

Sika® Sigunit® L-53 TH

August 2020, Version 01.01

021401011000000181

SikaSigunitL-53TH-en-MM-(08-2020)-1-1.pdf